



# CCW MiraDRAIN® 6200 Drainage Composites

## DESCRIPTION

CCW MiraDRAIN 6200 are high-performance, high-strength drainage composites consisting of a three-dimensional, high-impact polystyrene core, and a nonwoven filter fabric. CCW MiraDRAIN 6200 has the added benefit of a polymeric sheet adhered to the back of the core, to prevent the drainage core from die cutting the waterproofing membrane.

The filter fabric is bonded to the dimpled polystyrene core to minimize fabric intrusion. The fabric also prevents the passage of soil particles into the core, while allowing water to pass freely.

## TYPICAL USES

CCW MiraDRAIN 6200 are designed for use in high-flow, high-compressive strength, vertical drainage applications where single-sided subsurface drainage is needed.

CCW MiraDRAIN 6200 is designed for use over CCW Waterproofing Membranes, where added protection is needed. The high-strength polymeric film adhered to the flat side of the drainage core provides additional factors of safety from potential die cutting into the waterproofing membrane.

The flat side of CCW MiraDRAIN 6000/6200 fits directly against wall surfaces making them ideal for foundation walls, retaining walls, bridge abutments, and other similar structures. CCW MiraDRAIN 6000/6200 also serve as protection courses over CCW Waterproofing Membranes.

## FEATURES AND BENEFITS

- Relief of hydrostatic pressure buildup against subterranean surfaces
- High-flow drainage capacity - up to three times the flow capacity of aggregate or sand
- No-clogging drainage performance
- High compressive strength system withstands installation and in-situ earth stresses
- Enhancement of waterproofing system by channeling water away and providing a secondary water retention layer
- Cost-saving, lightweight, easy-to-install panels eliminate the need for aggregate

## TECHNICAL DATA

PROPERTY	METHOD	UNIT	TYPICAL VALUE
<b>CORE</b>			
Thickness	ASTM D1777	in (mm)	0.40 (10.16)
Compressive Strength	ASTM D1621 (mod)	psf (kPa)	15,000 (719)
Maximum Flow Rate <sup>1</sup>	ASTM D4716	gpm/ft <sup>2</sup> (l/min/m)	15 (188)
Installed Vertically <sup>2</sup>	ASTM D4716	gpm/ft <sup>2</sup> (l/min/m)	12.5 (155)
<b>FABRIC (DCN04)</b>			
Apparent Opening Size	ASTM D4751	US Std Sieve (mm)	40 (0.42)
Water Flow Rate	ASTM D4491	gpm/ft <sup>2</sup> (l/min/m)	200 (8,148)
Grab Tensile Strength	ASTM D4632	lbs (kN)	80 (0.36)
Grab Elongation	ASTM D4632	%	60
Puncture Strength	ASTM D4833	lbs (kN)	—
<b>SYSTEM</b>			
Performance Index	*	—	18,250
<small>All flow rates were tested at 3600 psf. * Drainage Performance Index is a function of ASTM D4833, D4632 and D1621 <sup>1</sup>In plane flow rate @ gradient of 1.0 <sup>2</sup>Installed flow rate with soil overburden at vertical gradient of 1.0</small>			

## INSTALLATION

### GENERAL INFORMATION

CCW MiraDRAIN prefabricated drainage panels may be installed in a variety of construction applications. They may be installed against retaining walls, foundation walls (both waterproofed and non-waterproofed), lagging systems and buttress/landfills. CCW MiraDRAIN can be cut with a utility knife or scissors. Slurries, shotcrete or concrete may be placed directly onto either side of the panels. The panels can terminate at the top of the footing and are flexible enough to form right angles to cover the top of the footing. CCW MiraDRAIN eliminates the need for a protection course over waterproofing systems. Native soils can be used over CCW MiraDRAIN. (Contact your local Carlisle Coatings & Waterproofing representative for specific guidelines).

### FOUNDATION WALLS / VERTICAL APPLICATIONS

The CCW MiraDRAIN panel can be installed in rows or columns with the fabric side toward the soil. Each method has its advantages depending on the criteria of the project as to which method is best.

When installing the CCW MiraDRAIN in rows:

- Place the longitudinal edge of the core against the wall so that it is flush with the wall footing.
- Attach subsequent panels in shingle fashion, placing the longitudinal edge of the upper panel over the flanged longitudinal edge of the lower panel.

When installing the CCW MiraDRAIN in columns:

- Start at the low point of the wall and attach the panel to the wall.
- Adjacent panels should be joined together with the lateral edge of the connecting panel placed over the flanged edge of the previous panel.

The fabric from the adjacent panels should overlap the preceding panel. The fabric can be adhered with CCW CAV-GRIP, mastic or duct tape. The top or terminal edge of the CCW MiraDRAIN should be sealed by wrapping the extra filter fabric around to the back side of the panel, and if there is insufficient fabric, the core shall be cut out from the fabric by a depth of 3 dimples to provide excess fabric for wrapping behind the core. This will prevent soil or other foreign construction materials from intruding into or behind the panels. A "set back" or "ledge" condition may be encountered on some construction applications. Where this condition exists, CCW MiraDRAIN panels should be installed beginning at the bottom of the wall and ending at the ledge. Subsequent courses of CCW MiraDRAIN should be installed flat against the upper wall portion and placed so that 4-6" (10-15 cm) extend down and over the lower edge. The overlapping CCW MiraDRAIN sections will be pushed flush against the wall during backfilling.

### **ATTACHMENT METHOD – NO WATERPROOFING MEMBRANE**

The CCW MiraDRAIN should be attached to non-waterproofed walls with CCW CAV-GRIP contact adhesive, CCW SecurTape tape or concrete nails. The CCW MiraDRAIN will be permanently secured upon completion of backfilling. Backfilling should be placed within two weeks. Backfill to at least 6" (15 cm) above the top edge of the CCW MiraDRAIN.

### **ATTACHMENT METHOD – USING CCW MIRADRI 860/861, CCW 525, CCW SURE SEAL, OR CCW-500R WATERPROOFING MEMBRANES**

The CCW MiraDRAIN should be attached with CCW CAV-GRIP contact adhesive or CCW SecurTape. Apply CAV-GRIP over entire surface of waterproofing membrane and mate the two surfaces together. The CCW MiraDRAIN will be permanently secured upon completion of backfilling. Backfilling should be placed as soon as possible. Backfill to at least 6" (15 cm) above the top edge of the CCW MiraDRAIN.

### **ATTACHMENT METHOD – USING CCW MIRA CLAY WATERPROOFING MEMBRANE**

The CCW MiraDRAIN should be attached over the CCW MiraCLAY membrane using concrete nails and washers.

### **ATTACHMENT METHOD – SOLDIER PILE**

## **SUPPORTED EXCAVATIONS**

The CCW MiraDRAIN should be secured with the appropriate fasteners for the substrate, i.e. concrete, masonry, wood or soil. Prevent concrete from flowing behind the CCW MiraDRAIN core by sealing the backside of the panel with duct tape or wood furring strip. Sealing the backside of the panel is not necessary if CCW MiraCLAY waterproofing membrane is applied over the CCW MiraDRAIN prior to pouring concrete or shotcreting. Voids in the soil or lagging that exceed 6" (150mm) across and 5" (12.5cm) deep must be filled to provide support for the CCW MiraDRAIN.

## **DRAINAGE COLLECTOR/DISCHARGE SYSTEM**

### **Collector Pipe**

Place CCW QuickDRAIN or collector pipe as required in design details. The CCW QuickDRAIN should be installed adjacent to the CCW MiraDRAIN. Care must be taken to ensure a continuous drainage path between the CCW QuickDRAIN and the CCW MiraDRAIN panels. For installations where a collector pipe is specified, encapsulate the collector pipe in a gravel bed with a supplemental section of filter fabric as a separator/filter.

## **DETAIL REQUIREMENTS**

For standard installation details, follow the CCW MiraDRAIN detail drawings. For non-standard installation instructions contact your local Carlisle Coatings & Waterproofing representative.

## **PACKAGING**

Packaging: CCW MiraDRAIN 6000 and 6200 are available in rolls of 4' x 50' (1.22 m x 15.24 m).

## **CAUTIONS / LIMITATIONS**

Limit ultraviolet exposure by backfilling within 7 days of installation. Any panels damaged during installation should be replaced by the installer. Limitations: CCW MiraDRAIN is resistant to chemicals in normal soil environments. However, some reagents may affect its performance. Carlisle Coatings & Waterproofing representatives should be consulted concerning the suitability of CCW MiraDRAIN in unusual soil environments.

## **LIMITED WARRANTY**

Carlisle Coatings & Waterproofing Incorporated (Carlisle) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Carlisle materials prove to contain manufacturing defects that substantially affect their performance, Carlisle will, at its option, replace the materials or refund its purchase price.

This limited warranty is the only warranty extended by Carlisle with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. Carlisle specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever.

The dollar value of Carlisle's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Carlisle material in question.